



Dry Film Adhesive 101 TS

Technical Data Sheet		
Thickness	.005"	
Estimated cost (large volume)	Call or email for pricing.	
Minimum Pressure	175 - 360 PSI	
Minimum Glue Line Temperature Under Full Temperature & Pressure	248° F	120° C
Bonding Temperature Under Full Temperature & Pressure	212° F	100° C
Base Resin	Blended Melamine	
Carrier	No Tear	
Color	Beige	
Fire Retardant	Yes	
Recommended bonding surfaces		
Cork, Cotton, Leather, Melamine, Paper, Wood Veneer, Chip Board, Wool, 2-ply Faces. Also bonds good with Aluminum, Carbon, Polyester & Phenolic.		

About our 101 TS

This glue film is based on a modified melamine resin. The carrier is extremely tear resistant making our 101 TS extreme durability as well as excellent bonding properties.